

Creep Strength

Average Stress, ksi, for 1% Total Creep in 10,000 Hours

| Alloy | Temperature, °F | | | | | | | | | |
|------------------------|-----------------|------|------|------|------|------|------|------|------|--------|
| | 1100 | 1200 | 1300 | 1400 | 1500 | 1600 | 1700 | 1800 | 1900 | 2000 |
| RA 253 MA [®] | 18 | 10 | 6.4 | 4.2 | 2.7 | 1.7 | 1.0 | 0.45 | 0.25 | (0.18) |
| RA330 [®] | - | 6.6 | - | 3.8 | - | 1.8 | - | 0.22 | - | - |
| RA 602 CA [®] | - | 26.8 | - | 9.4 | - | 2.38 | 1.52 | 0.96 | 0.59 | 0.33 |
| RA333 [®] | 19.5 | - | - | 5.3 | - | 2.45 | - | 0.77 | - | - |