

250 hour test in molten zinc, 850°F (454°C)					
alloy	original thickness		average metal loss		metal loss, ratio to AL-6XN®
	inch	(mm)	inch	(mm)	
AL-6XN	0.120	(3.05)	0.0056	(0.142)	1.00
556™	0.110	(2.79)	0.0034	(0.086)	0.6
1008	0.1328	(3.37)	0.0104	(0.264)	1.9
RA309	0.118	(3.0)	0.017	(0.432)	3.0
RA85H®	0.1164	(2.96)	0.0226	(0.574)	4.0
RA446	0.2008	(5.10)	0.0234	(0.594)	4.2
316	0.1188	(3.02)	0.044	(1.12)	7.9